

Technical Datasheet

Item Code: TP10000X | Rev.: 29-06-2022 | Ver: 3.2

POLIFILM TP 10

1K solvent-based joint and hole filler. Ready to mix with sanding dust from the floor



Description

POLIFILM TP 10 is a 1K solvent-based joint and hole filler. Ready to mix with sanding dust from the floor. Suitable for filling wooden floors or gaps between floor boards giving wooden floors smooth finish.

Characteristics

Mixture ratio	single-component
Application temperature	+10°C ÷ +25°C
Application	smooth trowel
Thinning (if necessary)	DNS 18 thinner
Coverage	n.a.
Dust dry	n.a.
Fingerprint dry	n.a.
Pot-Life	n.a.
Sanding	20-30' ⁽¹⁾
Overcoating without sanding	n.a.
Wood oxidation	n.a.
Pore filling	n.a.
Storage stability	1 year ⁽²⁾
Packaging	5 L - 12,5 L
Tool cleaning	DILUENTE DNE

1 at 20°C and 65% R.H.

2 in original sealed containers at temperatures between +10°C and +25°C

How to use

Shake well before use.

After having sanded the wood floor with 30 or 60 grit abrasive paper, apply using a smooth trowel POLIFILM TP 10 mixed with the wood dust coming from previous sanding with 100 grit abrasive paper. After finishing the smoothing, sand with 80 grit abrasive paper and proceed with the next sanding steps. If the floor has too many cracks, you must smooth it also after the 100 grit abrasive paper (always mixing TP 10 with wood dust coming from previous sanding with 100 grit abrasive paper).

Label elements

For more information about the safe use of the product it is recommended to consult the latest version of the Safety Data Sheet.

Web link

Be sure to have the latest version of this technical data sheet downloadable also from the following link:



http://www.chimiver.com/tds/EN_POLIFILM_TP_10.pdf

These information are given from the best of our knowledge and technical experience. They are of general character and not binding in any way our company. Every single case should be put to a practical test by the user who assumes the full responsibility of the final result of his work.